

## TECHNICAL DATA SHEET

ISSUED NO : FM-2019-3310

GRADE : EGG202

ISSUED DATE :

ITEM	UNIT	METHOD	SPEC.	RESULT
THICKNESS AVERAGE_ACT	μm	DIC	19.40 ~ 20.60	19.40
TENSILE STRENGTH_MD	kg/mm <sup>2</sup>	ASTMD882	Min 6.00	10.30
TENSILE STRENGTH_TD	kg/mm <sup>2</sup>	ASTMD882	Min 12.00	17.30
TENSILE ELONGATION_MD	%	ASTMD882	Max 200.00	176.00
TENSILE ELONGATION_TD	%	ASTMD882	Max 70.00	54.00
HAZE	%	ASTMD1003	Max 4.00	2.20
GLOSS_60°	-	ASTMD2457	Min 90.00	104.00
WETTING TENSION_INSIDE	dyne/cm	ASTMD2578	Min 44.00	52.00
WETTING TENSION_OUTSIDE	dyne/cm	ASTMD2578	Min 38.00	40.00
INI. SEAL. TEMP.	°C	DIC	90.00 ~ 120.00	90.00
SEALING. STRENGTH	g/25mm	DIC	Min 600.00	788.00
----- BLANK -----				

CERTIFY THE STATEMENT OF QUALITY TO BE TRUE AND CORRECT.