

TECHNICAL DATA SHEET

ISSUED NO : FM-2018-0568

GRADE: EGG242

ISSUED DATE :

ITEM	UNIT	METHOD	SPEC.	RESULT
THICKNESS AVERAGE_ACT	μm	DIC	23.28 ~ 24.72	23.28
TENSILE STRENGTH_MD	kg/mm ²	ASTMD882	Min 6.00	9.50
TENSILE STRENGTH_TD	kg/mm ²	ASTMD882	Min 12.00	16.40
TENSILE ELONGATION_MD	%	ASTMD882	Max 200.00	192.00
TENSILE ELONGATION_TD	%	ASTMD882	Max 70.00	53.00
HAZE	%	ASTMD1003	Max 4.00	4.00
GLOSS_60°	-	ASTMD2457	Min 90.00	100.00
WETTING TENSION_INSIDE	dyne/cm	ASTMD2578	Min 44.00	52.00
WETTING TENSION_OUTSIDE	dyne/cm	ASTMD2578	Min 38.00	39.00
INI. SEAL. TEMP.	°C	DIC	90.00 ~ 120.00	
SEALING. STRENGTH	g/25mm	DIC	Min 600.00	856.00
----- BLANK -----				

CERTIFY THE STATEMENT OF QUALITY TO BE TRUE AND CORRECT.