EUROPEAGROUPFILM

CRISTHER FILM | eurofilm21

TECHNICAL DATA SHEET

ISSUED NO : FM-2018-0569

GRADE: EGM252

ISSUED DATE :

ITEM	UNIT	METHOD	SPEC.	RESULT
THICKNESS AVERAGE_ACT	㎛	DIC	24.25 ~ 25.75	24.25
TENSILE STRENGTH_MD	kg/㎟	ASTMD882	Min 6.00	7.80
TENSILE STRENGTH_TD	kg/㎟	ASTMD882	Min 9.00	13.80
TENSILE ELONGATION_MD	%	ASTMD882	Max 210.00	200.00
TENSILE ELONGATION_TD	%	ASTMD882	Max 80.00	66.00
HAZE	%	ASTMD1003	Min 75.00	80.00
GLOSS_60˚	-	ASTMD2457	Max 9.00	8.90
WETTING TENSION_INSIDE	dyne/cm	ASTMD2578	Min 44.00	52.00
WETTING TENSION_OUTSIDE	dyne/cm	ASTMD2578	Min 38.00	40.00
INI. SEAL. TEMP.	℃	DIC	90.00 ~ 120.00	
SEALING. STRENGTH	g/25mm	DIC	Min 600.00	862.00
----- BLANK ----				

CERTIFY THE STATEMENT OF QUALITY TO BE TRUE AND CORRECT.